

Appl. No. 10/098,668
Reply to Office Action of July 31, 2003

Amendments to the Specification:

Page 53, Table 1: correction is made to the description of the Remarks for Radiation Image Conversion Panels 3 to 5 by replacing "Comp." with --Inv.--.

Accordingly, please delete Table 1 and replace it with the following new Table 1.

Table 1

Radiation Image Conversion Panel No.	Compression Treatment	Characteristics of Compliant Roller				Compression Condition		Remarks
		Roller Hardness (in degrees)	Roller Material	Surface Roughness (in μm)	Crown Length (in μm)	Temperature (in $^{\circ}\text{C}$)	Linear Pressure (in kN/cm)	
1	not carried out	-	-	-	-	-	-	Comp.
2	carried out	75	polyester resin	0.4	0	70	1	Comp.
3	carried out	85	polyester resin	0.3	0	70	1	Inv.
4	carried out	90	polyester resin	0.3	0	70	1	Inv.
5	carried out	95	polyester resin	0.2	0	70	1	Inv.
6	carried out	99	polyester resin	0.2	0	70	1	Comp.
7	carried out	100 or more	steel	0.05	0	70	1	Comp.
8	carried out	75	polyester resin	0.3	0	40	1	Inv.
9	carried out	75	polyester resin	0.3	0	140	1	Inv.

Inv.: Present Invention, Comp.: Comparative Example

RECEIVED
 OCT 23 2003
 TECHNOLOGY CENTER 2800